

BRIT STONE

EN 14411:2012 Annex G Group Bla UGL

TECHNICAL FEATURE	TEST METHOD	REQUIRED STANDARDS	BRIT STONE
SIZES AND LOOK OF THE TILE	ISO 10545-2	Length and width $\pm 0,6\%/\pm 2.0$ mm	Compliant
		Thickness $\pm 5\%/\pm 0.5$ mm	Compliant
		Straightness of sides $\pm 0,5\%/\pm 1.5$ mm	Compliant
		Rectangularity $\pm 0,5\%/\pm 2.0$ mm	Compliant
		Surface flatness $\pm 0,5\%/\pm 2.0$ mm Surface quality: 95% of tiles with no defaults	Compliant
WATER ABSORPTION	ISO 10545-3	≤ 0.5 %	0,06 % (average values referred to the last production)
AVERAGE BENDING STRENGTH	ISO 10545-4	35 N/mm ² min.	50,8 /mm ² (average values referred to the last production)
BREAKING STRENGTH	ISO 10545-4	Thickness $\geq 7,5$ mm: 1300 N min.	Compliant
RESISTANCE TO DEEP ABRASION	ISO 10545-6	175 mm ³ max.	Compliant
FROST RESISTANCE	ISO 10545-12	Required	Compliant
CHEMICAL RESISTANCE (DOMESTIC USE AND SWIMMING POOL CHEMICALS)	ISO 10545-13	min. UB	Compliant

Ragione Sociale: COEM S.p.A.

Sede Amministrativa:

42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32
tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

Sede Legale - Uffici Commerciali:

41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25
tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88
fax Export Dpt. +39 0536 83.26.11

Cap. Soc. € 12.000.000,00 i.v. - Reg. Impr. di Modena e C.F. 01927780369
R.E.A. Modena n° 252818 - Partita IVA: IT 01927780369

UNI EN ISO 9001:2015
UNI EN ISO 14001:2015
BS OHSAS 18001:2007



SISTEMI DI GESTIONE
CERTIFICATI



COEFFICIENT OF FRICTION	B.C.R.A. METHOD (D.M. no. 236 of 14/06/1989 of Italian Republic)		Unpolished/Textured: DRY: > 0.40 WET: > 0.40
ANTISLIP PROPERTIES	DIN 51130		Unpolished: R10 Textured: R11
ANTISLIP PROPERTIES ON WET SURFACES	DIN 51097		Textured: A+B
DYNAMIC COEFFICIENT OF FRICTION	DCOF (ANSI A137- 1:2012)		Unpolished: WET: 0.53 Textured: WET: 0.55 Half Polished: WET: 0.44

Valid only for items in 1st. choice.

On request we can certify conformity with standards that are not mentioned hereby

The special trims for the series, apart from those used for stair coverings, do not comply with the ISO EN 14411 standard.

Average values refer to tests which have been made on the unpolished surface if not otherwise specifically indicated.

Ragione Sociale: COEM S.p.A.

Sede Amministrativa:

42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32
tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

Sede Legale - Uffici Commerciali:

41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25
tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88
fax Export Dpt. +39 0536 83.26.11

Cap. Soc. € 12.000.000,00 i.v. - Reg. Impr. di Modena e C.F. 01927780369
R.E.A. Modena n° 252818 - Partita IVA: IT 01927780369

UNI EN ISO 9001:2015
UNI EN ISO 14001:2015
BS OHSAS 18001:2007



SISTEMI DI GESTIONE
CERTIFICATI

