

CARDOSO

EN 14411:2012 Annex G Group Bla UGL

TECHNICAL FEATURE	TEST METHOD	REQUIRED STANDARDS	CARDOSO	
SIZES AND LOOK OF THE TILE	ISO 10545-2	Length and width $\pm 0.6\%/\pm 2.0$ mm Thickness $\pm 5\%/\pm 0.5$ mm	Compliant Compliant	
		Straightness of sides $\pm 0.5\%/\pm 1.5$ mm Rectangularity $\pm 0.5\%/\pm 2.0$ mm Surface flatness $\pm 0.5\%/\pm 2.0$ mm	Compliant Compliant Compliant	
		Surface quality: 95% of tiles with no defaults		
WATER ABSORPTION	ISO 10545-3	≤ 0.5 %	0,07 % (average values referred to the last production)	
AVERAGE BENDING STRENGTH	ISO 10545-4	35 N/mm² min.	47,1 N/mm ² (average values referred to the last production)	
BREAKING STRENGTH	ISO 10545-4	Thickness ≥ 7,5 mm: 1300 N min.	Compliant	
RESISTANCE TO DEEP ABRASION	ISO 10545-6	175 mm ³ max.	Compliant	
FROST RESISTANCE	ISO 10545-12	Required	Compliant	
CHEMICAL RESISTANCE (ACID AND ALKALI LOW CONCENTRATION)	ISO 10545-13	According to the classification stated by the manufacturer	ULA Class	
CHEMICAL RESISTANCE (DOMESTIC USE AND SWIMMING POOL CHEMICALS)	ISO 10545-13	min. UB	Compliant	

Ragione Sociale: COEM S.p.A.
Sede Amministrativa:
42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32 tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

Sede Legale - Uffici Commerciali:

41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25 tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88 fax Export Dpt. +39 0536 83.26.11



UNI EN ISO 9001:2008 UNI EN ISO 14001:2004 BS OHSAS 18001:2007





.

COEFFICIENT OF FRICTION	B.C.R.A. METHOD (D.M. no. 236 of 14/06/1989 of Italian Republic)	Unpolished/Textured: DRY: > 0,40 WET: > 0,40
ANTISLIP PROPERTIES	DIN 51130	Unpolished: R10 Textured: R11
ANTISLIP PROPERTIES ON WET SURFACES	DIN 51097	Textured: A+B
DYNAMIC COEFFICIENT OF FRICTION	DCOF (ANSI A137- 1:2012)	Unpolished: WET: 0.56 Textured: WET: 0.59 Half polished: WET: 0.45

Valid only for items in 1st. choice.

On request we can certify conformity with standards that are not mentioned hereby

The special trims for the series, apart from those used for stair coverings, do not comply with the ISO EN 14411 standard.

Average values refer to tests which have been made on the unpolished surface if not otherwise specifically indicated.

Ragione Sociale: COEM S.p.A.
Sede Amministrativa:
42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32 tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

Sede Legale - Uffici Commerciali: 41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25 tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88 fax Export Dpt. +39 0536 83.26.11









PRODUCT COMPLIANT WITH LEED* REQUIREMENTS (LEADERSHIP IN ENERGY AND ENVIRONMENTAL DESIGN)



High content of recycled material

Ceramiche Coem is member of the U.S. Green Building Council (USGBC), the American association charged with implementing and regulating the construction of sustainable buildings by way of LEED® certification (Leadership in Energy and Environmental Design). As a result of their technical and structural characteristics, many of our products can help buildings improve their LEED® ratings, and have been certified for this purpose by the independent body CERTIQUALITY. Our products comply with the LEED® requirements for high content of recyclable material.

The index of refraction to light intrinsic to the porcelain stoneware support guarantees maximum thermal insulation and an optimum energy performance. Easy to clean as well as hygienic, our products contribute to enhancing the quality and safety of areas within buildings.

The requirements of eco-sustainability do not interfere with the aesthetic quality of the porcelain stoneware support, which is consistently at the avant-garde of design and technological innovation.

SERIES	COLORS	LEED* additional points for recycled material content Credits: MR 4.1 and 4.2	Additional points for external product certification Credits: ID 1.1-1.4	Additional points for S Reflectance Index (val obtained by correlatio Credit: SS 7.1	ues	Additional points for intrinsic technical features of the product Credits: ID 1.1-1.4	Additional points for Indigenous Raw Materials for projects realized within 500 miles from our production site Credit: MR 5.2	Additional points for not releasing Volatile Organic Compounds (VOC) Credit: EQ 4.2
CARDOSO	CORDA BEIGE GRIGIO CHIARO GRIGIO SCURO ANTRACITE	>30% pre_consumer 1 Point	1 Point	CORDA BEIGE GRIGIO CHIARO	1 Point	1 Point	2 Points	1 Point

Ragione Sociale: COEM S.p.A.
Sede Amministrativa:
42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32
tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

Sede Legale - Uffici Commerciali:41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25
tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88
fax Export Dpt. +39 0536 83.26.11



UNI EN ISO 9001:2008 UNI EN ISO 14001:2004 BS OHSAS 18001:2007

