

## CEMENTINE BLACK&WHITE

EN 14411: 2012 Annex G Group Bla GL

TECHNICAL FEATURE	TEST METHOD	REQUIRED MINIMUM STANDARDS	CEMENTINE BLACK&WHITE
SIZES AND LOOK OF THE TILE	ISO 10545-2	Length and width $\pm 0.6\% / \pm 2.0 \text{ mm}$ Thickness $\pm 5\% / \pm 0.5 \text{ mm}$ Straightness of sides $\pm 0.5\% / \pm 1.5 \text{ mm}$ Rectangularity $\pm 0.5\% / \pm 2.0 \text{ mm}$ Surface flatness $\pm 0.5\% / \pm 2.0 \text{ mm}$ Surface quality:95% of tiles with no defaults	Compliant Compliant Compliant
WATER ABSORPTION	ISO 10545-3	≤ 0.5 %	0.12 % (average values referred to the last production)
AVERAGE BENDING STRENGTH	ISO 10545-4	$35 \text{ N/mm}^2 \text{ min.}$	44.8 N/mm <sup>2</sup> (average values referred to the last production)
BREAKING STRENGTH	ISO 10545-4	Thickness ≥ 7,5 mm: 1300 N min.	Compliant
RESISTANCE TO SURFACE ABRASION	ISO 105 <del>4</del> 5-7	State the PEI rate and covered cycles	CLASS 4 (2100 rotations)
CRAZING RESISTANCE	ISO 10545-11	Required	Compliant
FROST RESISTANCE	ISO 10545-12	Required	Compliant
STAIN RESISTANCE	ISO 10545-14	Min. Class 3	Class 5
CHEMICAL RESISTANCE (ACID AND ALKALI LOW CONCENTRATION)	ISO 10545-13	According to the classification stated by the manufacturer	GLA Class

Ragione Sociale: COEM S.p.A.

Sede Amministrativa: 42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32 tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

Sede Legale - Uffici Commerciali:

41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25 tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88 fax Export Dpt. +39 0536 83.26.11







CHEMICAL RESISTANCE  (DOMESTIC USE AND SWIMMING POOL CHEMICALS)	ISO 10545-13	Min. GB	Compliant
_			
	B.C.R.A. METHOD		DDV. > 0.40

COEFFICIENT OF FRICTION	B.C.R.A. METHOD (D.M. no. 236 of 14/06/1989 of Italian Republic)	DRY: > 0,40 WET: > 0,40
ANTISLIP PROPERTIES	DIN 51130	R9
DYNAMIC COEFFICIENT OF FRICTION	DCOF ANSI A137-1:2012	WET: 0.68

Valid only for items in 1<sup>st.</sup> choice.

On request we can certify conformity with standards that are not mentioned hereby.

The special trims for the series, apart from those used for stair coverings, do not comply with the ISO EN 14411 standard.

Average values refer to tests which have been made on the unpolished surface if not otherwise specifically indicated.

Ragione Sociale: COEM S.p.A. Sede Amministrativa: 42014 Roteglia (RE) - Italy - Via Stradone Secchia, 32 tel. +39 0536 99.31.11 - fax +39 0536 99.32.48

41042 Fiorano Modenese (MO) - Italy - Via Cameazzo, 25 tel. +39 0536 99.35.11 - fax Comm. Italia +39 0536 99.35.88 fax Export Dpt. +39 0536 83.26.11



