

AZULEJ / technical features

norma standard	caratteristiche features	valore prescritto value required	azulej
ISO 10545/3	assorbimento d'acqua water absorption	<0,5%	0,04%
ASTM C373		<0,5%	0,04%
EN 101	durezza superficiale (scala mohs) surface hardness (scala mohs)	> 5	6
ISO 10545/9	resistenza agli sbalzi termici resistance to thermal shock	nessuna alterazione visibile no visible alteration	resiste resistant
ASTM C484		no samples must show visible defects	unaffected
ISO 10545/12	resistenza al gelo frost resistance	nessuna alterazione visibile no visible alteration	resiste resistant
ASTM C1026		unaffected	unaffected
ISO 10545/13	resistenza agli attacchi chimici resistance to chemical attacks	nessuna alterazione visibil no visible alteration	resiste resistant
ASTM C650			unaffected
ISO 10545/4	sforzo di rottura (N) breaking strength (N)	Sp \geq 7,5 min 1300	2525,1
DIN 51130 - 04		valori medi 6° ÷ 10° 10° ÷ 19° 19° ÷ 27° 27° ÷ 35° > 35°	R9 R10 R11 R12 R13
ASTM C1028		> 0,60	dry 0,85 wet 0,77

LEED CERTIFICATION 4.1 14,5% recycled material (pre-consumer)

sistema produttivo con certificazione ambientale ISO 14001 : 2004
environmental management system ISO 14001 : 2004

AZULEJ / packing

	pz-mq pcs-sqm	pz-scat. pcs-box	mq-scat. sqm-box	scat.-pal. box-pal.	kg-scat. kg-box	kg-pal. kg-pal.	mq-pal sqms-pal
20·20	25	24	0,96	72	20,95	1508	69,12
pattern 20·20	25	24	0,96	72	20,95	1508	69,12
combination 20·20	25	27	1,08	48	23,45	1126	51,84
battiscopa 4,7·20	-	10	2 ml	-	2,15	-	-



V1
variazione uniforme
uniform variation